



Zintek Srl
Via delle Industrie 22
30175 Porto Marghera Venezia IT

tel +39 041 2901866
fax +39 041 2901834
zintek@zintek.it
www.zintek.it

1 - FOREWORD: ZINTEK® IN THE CONSTRUCTION INDUSTRY

Zinc laminate has been used for many years in the construction industry, so as to make it, on a European level, the most popular non-ferrous material used for cladding and covering solutions. Zintek® is a high-quality zinc-copper-titanium alloy. The alloy must be produced with Z1 quality zinc with 99.995% pure Zinc in accordance with European standard EN 1179 with the addition of alloy elements that improve the characteristics of the laminate: Titanium increases its resistance to permanent deformation over time; Copper increases the tensile strength of the material.

The combination of both materials reduces the expansion coefficient of the alloy. The chemical-physical characteristics of zintek® allow optimal workability and weldability. Its resistance to atmospheric corrosion makes it possible to cut maintenance and repair costs, to enhance the value of building architecture within an extremely wide range of contexts. In fact, zintek® is a leading company within this sector thanks to the following factors:

- Respect for the environment;
- Affordability compared to other non-ferrous metals used in similar applications.
- Low-maintenance with opportune and coherent planning.
- Exceptional durability.
- Attractive aesthetic appearance.

2 – AIM OF TECHNICAL SPECIFICATION

This document aims to define the characteristics of zintek®, its range of use, functionality, performance, proper packaging, transport, storage methods, safety and compliance with standards and laws.

3 – SPECIFIC STANDARDS

Zintek® complies with the following standards:

- UNI EN 988: “Zinc and Zinc alloys – Specifications for rolled flat products and for building purposes”
- UNI EN 14783: “Fully-supported metal sheets and strips for roofing, external cladding and internal lining”

In standard UNI EN 988, specifications are provided for Zinc-Copper-Titanium alloy rolled flat products used in the construction industry and supplied in the form of coils, sheets or strips.

In standard UNI EN 14783, specifications and testing methods are provided for metal coils, strips and rolled flat sheets as well as components produced for fully-supported roofing, external cladding and internal lining purposes. In order to comply with this standard, it CE-marking is mandatory.

For further clarification, see the definition specified in the FPC (Factory Production Control) relating to CE-marking with regard to

Pre-patinated, expanded zintek® TECHNICAL SPECIFICATIONS (ref. - DOP. B05)

the term “fully-supported””: *Condition whereby it is necessary for there to be a load-bearing structure underneath the panel; or rather, panels supported by a continuous self-supporting structure (EN 501:1996) during the installation stage, so that the flat bottom parts are reinforced and therefore structurally supported (therefore, the product is not self-supporting as in EN 14782).*

Norma zintek®: UNI EN 988

a) composizione in %

Element	Min. content	Max. content
Cu	0.080	1.000
Ti	0.060	0.200
Al	-----	0.015
Zn (1)	remainder	remainder

(1) Z1-quality zinc (see UNI EN 1179 table)

Zintek standard®: UNI EN 988

b) Mechanical characteristics

unit load deviation from proportionality	0.2% Rp 0.2 N/mm ²	100 min
Tensile strength	Rm N/mm ²	150 min
Elongation percentage at break	A50mm %	35 min
Creep strain rate percentage	%	0.1 max
Minimum hardness	HV	45

Calculation of the masses

Nominal thickness mm	Approximate mass Kg/m ²
0.80	5.8
1.00	7.2

4 – INSTALLATION CONDITIONS AND STORAGE

Products in zintek® must be stored in a dry, ventilated location. It is necessary to keep the level of humidity under control. Stocks of these products must be protected against humidity. Therefore, storage outdoors must be avoided, and coils or profiles must be directly covered, unless ventilated spaces are left between one item and another. Moreover, it is necessary to avoid the formation of condensation if the temperature inside the warehouse drops below dew point.

The laminate must not be processed at temperatures below 10°C. It is advisable to carry out processing activities after having brought the temperature of the laminate up to the minimum value stated.

Details relating to the installation stage are given in the manual entitled “*Sviluppo in Architettura*” (“*Development in Architecture*”).

However, estimates and applications are contents provided inside on-line specifications, available on the www.zintek.it website.

5 - CHARACTERISTICS

Physical and technological characteristics		
Description	Unit of measurement	Value
Density	Kg/dm ³	7.14
Melting point	°C	419
Specific heat at 20 °C	kJ/kg °C	0.401
Thermal conductivity at 20 °C	W/m K	109
Electrical conductivity at 20 °C	m/ohm mm ²	17
Thermal expansion coefficient parallel to rolling (lamination)	mm/m °C	0.022
Thermal expansion coefficient transversal to rolling (lamination)	mm/m °C	0.017
Re-crystallisation limit	°C	> 300
Elastic modulus	N/mm ²	> 80000
Erichsen Cupping Test value	mm	7 – 9
Lengthwise Bend test at 180° 20 °C	n°	3 (min.)
Crosswise Bend test at 180° 20 °C	n°	5 (min.)
Stiffness	%	40 – 55
Non-magnetic		
Fireproof		
CE-marking method (UNI EN 14783)	-	System 3

SURFACE APPEARANCE: The appearance of pre-patinated zintek® is a shade of grey that is very similar to natural zintek® once it has been oxidised.

When exposed to adverse weather conditions, its surface turns a slightly darker colour that remains stable over time, guaranteeing a pleasant aesthetic appearance.

The oxidation process may result in a slight change of shade without causing any significant changes to the surface itself. In some cases, where the aggressiveness of the atmosphere is particularly intense, whitish rings may appear on the zintek® surface that, in any case, does not alter the material consistency of the laminate.

6 - PERFORMANCE

As for zintek® performance, see the section on CE-marking and the relative DOP documentation.

7 – SERVICE LIFE, BEHAVIOUR AFTER CONTACT WITH CHEMICAL SUBSTANCES AND CORROSION RESISTANCE

Contact with acid and alkaline substances must be avoided.

When different metals come into contact with each other, they can be damaged due to their potential difference, therefore, the zintek® laminate must never come into contact with copper and its alloys (such as brass), neither directly nor indirectly, for example, through the flow of rainfall that passes from covering solutions or copper items to others made of zintek® laminates.

Durability	
Environment	Durability
Countryside	Over 100 years
Industrial city	60 years
Industrial cluster	40 years
Seaside city	From 40 to 60 years

8 – BEHAVIOUR ACCORDING TO CHANGES IN TEMPERATURE

The laminate is not affected by changes in temperature that occur after processing and installation. However, it is advisable to use hot air heaters in order to carry out bending operations when the temperature of the laminate is below 10 °C.

Its melting point is at approximately 419 °C and its re-crystallisation limit, essential to perform the brazing technique, is at 300 °C.

It is fireproof, resistant to UV-rays and

9 - SUPPLY CHARACTERISTICS

Expanded laminates

Dimensions as per specific item.

Available thicknesses

0,80 – 1,00 mm

Upon request, other thicknesses are also available up to a maximum of 1.50 mm.

Permeability

Zintek® is impermeable to water, air and steam. The expanded zintek® laminate is permeable to water, air and steam.

Tolerance

Thickness: The maximum deviation compared to the nominal thickness ordered must not exceed +/- 0.03 mm.

Width: The maximum deviation compared to the nominal width ordered must not exceed 0/+2 mm.



Length: The maximum deviation compared to the nominal length of the metal sheet or strip ordered must never exceed 0/+ 10 mm.

10 – PACKAGING AND DELIVERY

For each transport operation, an appropriate dry, well-ventilated area must be guaranteed. The loading and unloading of vehicles must be carried out in a dry and/or indoor environment. It is necessary to avoid transporting the material on humid pallets and to make sure that the surface protection is adequate so as to avoid any potential damage being caused.

11 – COMPLIANCE WITH UNI EN 14783

Zintek hereby declares that it is in conformity with standard UNI EN 14783 with the following characteristics:


<p>Zintek Srl, via delle Industrie 22 30175 Porto Marghera (Venice, Italy)</p> <p>14</p>
<p>EN 14783:2013</p> <p>A fully-supported metal product for roofing, external cladding, internal lining and tinsmithery purposes</p> <p>Material: Pre-patinated, expanded zintek®.</p>  <p>Dimensions: As per specific item.</p> <p>Nominal thickness: from 0.80 mm to 1.50 mm - EN 501.</p> <p>Water permeability: NPD.</p> <p>Dimensional tolerances: Thickness: +/- 0.03 mm; Width: 0/+2 mm; Length: 0/+ 10 mm; Straightness: NPD; Flatness: NPD.</p> <p>Steam and air permeability: NPD.</p> <p>Release of dangerous substances: NPD.</p> <p>Reaction to fire: Class A1-s1-d0.</p> <p>Outdoor fire behaviour: Class B_{ROOF} (I2).</p> <p>Durability: NPD.</p>

12 – MAINTENANCE

The maintenance of zintek® products must be correlated and conducted in accordance with:

- Mandatory documents pursuant to Ministerial Decree dated 17th January 2018 “Technical Building Standards” - chapter 10;
- UNI 10372 “Instructions for the design, execution and maintenance of roofs made from metal sheeting” – chapter. 11;
- UNI 10724 “Rainwater collection and drainage systems”- chapter 5.

(The validity of the NTC 2018 is limited to Italy. As for EU and extra-EU countries, the respective national laws apply).

The maintenance document, both planned and managed under surveillance, must include, at the designer’s discretion, the following stages, regardless of the base material specified in this document, in any case, considering the parts of the building affected by maintenance:

Building parts:	Activities:	Frequency:
General for all elements	Visual inspection (damage, dirt deposits, growth of moss and vegetation, connections and joints)	Yearly
	In-depth precautionary check	3-5 years
Profiled elements for covering solutions and facades (seamed, shingles, slats, coffered, etc.)	Maintenance (replacement of worn or damaged elements, cleaning operations to remove dirt and material deposits)	3-5 years
Gutters and outflow pipes	Check for obstructions	Every 6 months, after every storm or torrential downpour
	Check for deformations	Yearly, during the winter
	Removal of ice obstructing the rainwater channelling areas	Yearly, during the winter
	Check for humidity and discoloration of the adherent facades	6 months
Roof water drainage system	Inspection – securing of the functional capacity	Yearly
Connections and joints	Inspection of the tightening torque and seals between elements.	Yearly

13 – SAFETY

Just like any other metal sheet, also zintek®, due to its handling and processing (cutting and bending), is subject to mechanical risks such as cuts, lacerations and abrasions. For these reasons, workers must protect their limbs and eyes during assembly and installation with PPEs bearing CE-markings that guarantee at least the following degree of protection:

- Mechanically-resistant gloves with a minimum level of protection (in the following order: abrasion, cutting, tearing and perforation): 2332;
- Mechanically-resistant overalls or work clothes;
- S3 category safety shoes;

- Polycarbonate goggles, field of use: 4, type: S, class: 2, filtering action code: 5.

Other processing and installation risks to be assessed include:

- Scalds and burns after coming into contact with sheets exposed to sources of heat for a long time (or solar radiation);
- Slips and falls, in particular on sloping roofs, during winter months for the possible formation of thin layers of ice over zintek®.